

PRODUCT DATA SHEET

Sikacrete[®]-114

FREE FLOWING MICRO-CONCRETE FOR GROUTING AND REPAIR

DESCRIPTION

Sikacrete[®]-114 is a one component, free-flowing, high strength, non-shrink, cement based micro-concrete with a maximum aggregate size of 10 millimeter. Suitable for use in hot and tropical climatic conditions.

USES

Sikacrete[®]-114 is used for the structural repair of deteriorated concrete. It is ideal for casting sections or members where the volumes required are too large for conventional grouts, and too small and inaccessible for normal concreting applications. A typical application is the re-profiling of damaged concrete members, using formwork. Also suitable for base plate grouting where thickness exceeds 100 millimetre.

CHARACTERISTICS / ADVANTAGES

- One component, requires the addition of water only
- Reduced waste and risk of mixing failures
 - Easy to mix, apply and finish
 - Economical
 - Excellent adhesion
 - Shrinkage compensated
 - Rapid strength development
 - Compatible with the properties of typical concrete
 - Vapour permeable

PRODUCT INFORMATION

Composition	Portland cement, selected fillers and aggregates, special additives
Packaging	40 kg bag
Appearance / Colour	Grey powder
Shelf life	12 months minimum from date of production
Storage conditions	Store in original unopened packaging in cool and dry condition between 5 °C and 35 °C. Protect from direct sunlight, heat and moisture.
Density	~2.4 kg/l (25 °C) (fresh mortar)
Maximum grain size	Max. 10 mm

TECHNICAL INFORMATION

Compressive strength	1 Day	7 Day	28 Day	(ASTM C109)
	4.2 L water / 40 kg at 25 °C	≥ 35 N/mm ²	≥ 45 N/mm ²	
Modulus of elasticity in compression	≥ 33 000 N/mm ²			(ASTM C 469-94)
Tensile strength	~5 N/mm ²			(ASTM C307)
Tensile adhesion strength	> 1.5 N/mm ² (concrete failure)			(BS 1881)
Water absorption	~2.3 % (28 d)			(BS 1881)

APPLICATION INFORMATION

Mixing ratio	4.0 - 4.25 L of water per 40 kg bag		
Yield	~18.4 L / 40 kg bag		
Layer thickness	Min. 50 mm per pour Max. 500 mm per pour	(Min. 100 mm for baseplate grouting)	
Ambient air temperature	+5 °C min. / +35 °C max.		
Substrate temperature	+5 °C min. / +35 °C max.		
Pot Life	~2 h (25 °C)		

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Ensure formwork is secure and watertight to prevent movement and leaking during placing and curing.
- At high ambient temperatures use chilled water for mixing to keep grout temperature below 30 °C.
- In hot weather, base plates and foundations must be shaded from direct sunlight.
- For additional information on Sikacrete®-114 or other grouting materials contact Sika Technical Department.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete surfaces should be clean, sound, rough and free from oil, grease, cement laitance and all loosely adhering particles.

Absorbent surfaces should be saturated thoroughly with clean water.

Metal surfaces (iron and steel) should be free from scale, rust, oil and grease.

BONDING AGENT AND STEEL PROTECTION

Embedded reinforcing steel should be free from scale, rust, oil and grease, and treated with a suitable anti-corrosion coating such as SikaTop® Armatec® 110 EpoCem®.

The application of a suitable bonding agent, such as Sikadur®-32 LP or SikaTop® Armatec® 110 EpoCem®, will improve adhesion on large areas or where particularly dense concrete substrates are involved.

MIXING

Always empty the full contents of the bag into a suitable mixer.

Mix dry for 3 minutes before adding the water. Add 4.0 to 4.25 litre of water per 40 kilogram bag. Best mixed in a forced action mixer.

Do not mix by hand or mix part bags!

For best results, first add 3.5 to 3.8 litre of water and mix for at least 3 minutes or until the larger aggregate has thoroughly dispersed and a uniform, free flowing consistency is obtained. Then add remaining water and mix for additional 2 minutes.

APPLICATION

Dampen all concrete surfaces thoroughly with clean water prior to application.

Before pouring, however, let the mixed grout stand for 2 to 3 minutes after mixing with the mixing water to allow entrapped air to escape.

Maintain sufficient hydrostatic head to keep the product flowing.

Provide channels for the air to escape during grouting. Protect from rain until initial set has been achieved.

PRODUCT DATA SHEET

Sikacrete®-114

December 2020, Version 01.01

020302030100000004

CURING TREATMENT

Treat exposed surfaces with Antisol-WB curing compound or use other approved curing methods such as polyethylene sheeting or wet hessian.
Do not commence fogging until final set has been reached.

CLEANING OF EQUIPMENT

Clean equipment and mixer after application with water.
Hardened material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Iraq (Sika Trading L.L.C.)

Erbil / Baghdad / Basra

Tel: +96 477 303 74451

info@iq.sika.com

irq.sika.com

PRODUCT DATA SHEET

Sikacrete®-114

December 2020, Version 01.01

020302030100000004

Sikacrete-114-en-IQ-(12-2020)-1-1.pdf