

PRODUCT DATA SHEET

Sikadur®-30 LP

Thixotropic adhesive for bonding reinforcement

DESCRIPTION

Sikadur®-30 LP is a thixotropic, structural 2-component adhesive, based on a combination of epoxy resins and especially designed for use at higher temperatures between +25 °C and +55 °C.

USES

Sikadur®-30 LP may only be used by experienced professionals.

Adhesive for bonding structural reinforcement, particularly in structural strengthening works. Especially for the following uses:

- Sika® CarboDur® Plates to concrete, brickwork, timber and steel (for details see the Sika® CarboDur® Product Data Sheet, the “Method Statement for Sika® CarboDur® Externally Bonded Reinforcement” Ref: 850 41 05 and the “Method Statement for Sika® CarboDur® Near Surface Mounted Reinforcement” Ref: 850 41 07).
- Steel plates to concrete (for details see the relevant Sika Technical information).

CHARACTERISTICS / ADVANTAGES

Sikadur®-30 LP has the following advantages:

- Long pot life
- High temperature resistance at elevated curing temperatures
- Easy to mix and apply
- No primer needed
- High creep resistance under permanent load
- Very good adhesion to concrete, masonry, stonework, steel, cast iron, aluminium, timber and Sika® CarboDur® Plates
- Hardening is not affected by high humidity
- High strength adhesive
- Thixotropic: non-sag in vertical and overhead applications
- Hardens without shrinkage
- Different coloured components (for mixing control)
- High initial and ultimate mechanical resistance
- High abrasion and shock resistance
- Impermeable to liquids and water vapour

APPROVALS / CERTIFICATES

- Structural bonding product for bonded plate reinforcement according to EN 1504-4:2004, Declaration of Performance 0202060400100000031001, certified by notified factory production control certification body 0921, certificate of conformity of the factory production control 0921-CPR-2054, and provided with the CE marking.

PRODUCT INFORMATION

Composition	Epoxy resin	
Packaging	6 kg (A+B)	Pre-batched unit pallets of 480 kg (80 x 6 kg)
Colour	Component A: white Component B: black	

Component A + B mixed: light grey

Shelf life	24 months from date of production
Storage conditions	Store in original, unopened, sealed and undamaged packaging in dry conditions at temperatures between +5 °C and +30 °C. Protect from direct sunlight.
Density	1.65 kg/l ±0.1 kg/l (components A+B mixed) (at +23 °C)

TECHNICAL INFORMATION

Compressive strength	Curing time	Curing temperature		(DIN EN 196)
		+25 °C	+55 °C	
	12 hours	–	~90 N/mm ²	
	1 day	~75 N/mm ²	~100 N/mm ²	
	3 days	~85 N/mm ²	~110 N/mm ²	

Modulus of elasticity in compression	~10 000 N/mm ² (at +25 °C)	(ASTM D 695)
---	---------------------------------------	--------------

Tensile strength in flexure	Curing time	Curing temperature		(DIN EN 196)
		+25 °C	+55 °C	
	1 day	~12 N/mm ²	~38 N/mm ²	
	3 days	~20 N/mm ²	~40 N/mm ²	
	7 days	~25 N/mm ²	~42 N/mm ²	

Tensile strength	Curing time	Curing temperature		(ISO 527)
		+25 °C	+55 °C	
	1 day	–	~26 N/mm ²	
	3 days	~14 N/mm ²	~28 N/mm ²	
	7 days	~17 N/mm ²	~28 N/mm ²	

Modulus of elasticity in tension	~10 000 N/mm ² (at +25 °C)	(ISO 527)
---	---------------------------------------	-----------

Tensile adhesion strength	Curing time	Substrate	Curing temperature		(EN ISO 4624)
			+25 °C	+55 °C	
	1 day	Concrete	>4 N/mm ² (Concrete fracture)	>4 N/mm ² (Concrete fracture)	
	1 day	Steel	15 N/mm ²	25 N/mm ²	
	3 days	Steel	22 N/mm ²	28 N/mm ²	

Shear strength	Curing time	Curing temperature			(FIP 5.15: Fédération Internationale de la Précontrainte)
		+25 °C	+44–55 °C	+80 °C	
	>1 hour	–	–	*17 N/mm ²	
	7 days	*7 N/mm ²	~19 N/mm ²	–	

*(DIN EN 1465)

Shrinkage	0.04 %	(FIP: Fédération Internationale de la Précontrainte)
------------------	--------	--

Coefficient of thermal expansion	2.5 x 10 ⁻⁵ 1/K (Temperature range: –20 °C to +40 °C)	(EN 1770)
---	--	-----------

Glass transition temperature	Curing time	Curing temperature	TG	(EN 12614)
	3 days / 1 day	+23°C / +80 °C	+90 °C	
	3 days / 1 day	+23°C / +50 °C	+80 °C	
	30 days	+30 °C	+70 °C	

Heat deflection temperature	Curing time	Curing temperature	HDT	(FIP 5.10: Fédération Internationale de la Précontrainte, ASTM D 648)
	2 hours	+80 °C	+84 °C	
	7 days	+55 °C	+82 °C	
	7 days	+23 °C	+55 °C	

Service temperature	-40 °C to +45 °C (when cured at > +23 °C) -40 °C to +72 °C (when cured > 2 hours at +80 °C within 7 days)
---------------------	--

SYSTEMS

System structure	Sika® CarboDur® System: For Application Details of Sika® CarboDur® plates with Sikadur®-30 LP, see the "Method Statement for Sika® CarboDur® Externally Bonded Reinforcement" Ref: 850 41 05 and the "Method Statement for Sika® CarboDur® Near Surface Mounted Reinforcement" Ref: 850 41 07
------------------	---

APPLICATION INFORMATION

Mixing ratio	Component A : Component B = 3 : 1 by weight or volume Only mix complete pre-batched units of Sikadur®-30 LP.			
Layer thickness	30 mm max.			
Sag flow	On vertical surfaces it is non-sag up to 3–5 mm thickness at +55 °C. (FIP: Fédération Internationale de la Précontrainte)			
Squeezability	5 500 mm ² at +25 °C at 15 kg (FIP: Fédération Internationale de la Précontrainte)			
Product temperature	Sikadur®-30 LP must be applied at temperatures between +20 °C and +40 °C.			
Ambient air temperature	+25 °C min. / +55 °C max.			
Dew point	Beware of condensation. Substrate temperature during application must be at least 3 °C above dew point.			
Substrate temperature	+25 °C min. / +55 °C max.			
Substrate moisture content	Max. 4 % pbw When applied to mat damp concrete, brush the adhesive well into the substrate.			
Pot Life	Temperature	Potlife	Open time	(FIP: Fédération Internationale de la Précontrainte)
	+25 °C	~90 minutes	~120 minutes	
	+55 °C	~30 minutes	~60 minutes	

The potlife begins when the resin and hardener are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the potlife. To obtain longer workability at high temperatures, the mixed adhesive may be divided into portions. Another method is to chill components A+B before mixing them (not below +5 °C).

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Sikadur® resins are formulated to have low creep under permanent loading. However, due to the creep behavior of all polymer materials under load, the long term structural design load must account for creep. Generally the long term structural design load must be

lower than 20–25 % of the failure load.

A structural engineer must be consulted for load calculations for the specific application.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

See the Product Data Sheet of Sika® CarboDur® Plates and Sika® CarboDur® BC rods.

SUBSTRATE PREPARATION

See the “Method Statement for Sika CarboDur® Externally Bonded Reinforcement” Ref: 850 41 05 and the “Method Statement for Sika CarboDur® Near Surface Mounted Reinforcement” Ref: 850 41 07.

MIXING

Pre-batched units:

Mix components A+B together for at least 3 minutes with a mixing spindle attached to a slow speed electric drill (max. 300 rpm) until the material becomes smooth in consistency and a uniform grey colour.

Avoid aeration while mixing. Then, pour the whole mix into a clean container and stir again for approx. 1 more minute at low speed to keep air entrapment at a minimum. Mix only that quantity which can be used within its potlife.

APPLICATION METHOD / TOOLS

See the “Method Statement for Sika® CarboDur® Externally Bonded Reinforcement” Ref: 850 41 05 and the “Method Statement for Sika® CarboDur® Near Surface Mounted Reinforcement” Ref: 850 41 07.

PRODUCT DATA SHEET

Sikadur®-30 LP

December 2020, Version 03.01

020206040010000003

CLEANING OF EQUIPMENT

Clean all tools and application equipment with Sika® Colma Cleaner immediately after use. Hardened / cured material can only be mechanically removed.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Iraq (Sika Trading L.L.C.)

Erbil / Baghdad / Basra

Tel: +96 477 303 74451

info@iq.sika.com

irq.sika.com

PRODUCT DATA SHEET

Sikadur®-30 LP

December 2020, Version 03.01

020206040010000003