

PRODUCT DATA SHEET

SikaBit® T-1150 PG SA

4 MM TORCH-ON, SHEET WATERPROOFING AND ROOFING MEMBRANE BASED ON ATACTIC POLY PROPYLENE (APP) MODIFIED, REINFORCED BITUMEN 150 G/M2, WITH POLYETHYLENE FILM ON BOTH SIDES

DESCRIPTION

SikaBit® T-1150 PG SA is a standard torch-on sheet waterproofing membrane. It is based on APP (Atactic Poly-Propylene) modified bitumen, reinforced with a 150 g/m² polyester non-woven fabric and, faced with a polyethylene film on both the top surface and the reverse to ease installation works.

Suitable for use in hot and tropical climatic conditions.

USES

SikaBit® T-1150 PG SA may only be used by experienced professionals.

It is used a waterproofing membrane for protection of various substrates in a wide range of applications.

- Waterproofing and damp-proofing of the exterior walls of basements against percolating water and damp soil
- Waterproofing of retaining walls
- Wet areas
- Waterproofing on flat roofs under protective layers or ballast
- Waterproofing on balconies, terraces and wetrooms under tiles

CHARACTERISTICS / ADVANTAGES

- Resistant to ageing
- Resistant to weathering
- Good tensile strength and elongation
- High resistance to water vapour
- Good dimensional stability
- Flexible at low temperatures
- Easy to install using the torch-on method
- Suitable as top layer for multilayer installations
- Good resistance to mechanical impact

PRODUCT INFORMATION

Composition	Atactic Polypropylene Modified Bitumen
Packaging	Roll size: 1.00 m (roll width) x 10.00 m (roll length). 23 rolls per pallet.
Appearance / Colour	Rolled sheet membrane, reinforced with polyester non-woven fabric with Polyethylene film on both sides for ease of installation Colour: Black
Shelf life	2 years minimum from date of production if stored properly in original unopened packaging.
Storage conditions	Rolls must be stored in their original package, in vertical position and un-

der cool and dry conditions between temperatures of +5 °C and +35 °C. They must be protected from direct sunlight, rain, snow and ice.

Length	10 m ± 1 %	
Width	1.0 m ± 1 %	
Effective thickness	4 mm ± 0.2 mm	(ASTM D5147)
Mass per unit area	4.5 kg/m ² ± 10 %	(EN 1849-1)

TECHNICAL INFORMATION

Resistance to impact	> 300 mm	(EN 12691)	
Tensile strength	Longitudinal	~600 N/50 mm	(ASTM D5147)
	Transversal	~450 N/50 mm	
Elongation	Longitudinal	~40 %	(ASTM D5147)
	Transversal	~40 %	
Tear strength	Longitudinal	≥ 500 N	(ASTM D5147)
	Transversal	≥ 350 N	
Joint shear resistance	Longitudinal	~600 N/50 mm	(EN 12317-1)
	Transversal	~450 N/50 mm	
Foldability at low temperature	0 °C	(EN 1109)	
Watertightness	Method A	≥ 60 kPa	(EN 1928-1)
	Method B	≥ 400 kPa	
Service temperature	0 °C min. / +35 °C max.		

APPLICATION INFORMATION

Ambient air temperature	+5 °C min. / +50 °C max.
Substrate temperature	+5 °C min. / +65 °C max.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Not resistant to root penetration.
Ambient Maximum Temperature of Liquids + 35 °C.
Avoid damage to previously installed membranes during the torch-on of further layers of sheet membrane. The water tightness of the structure must be tested and approved after completion of the membrane installation works according to the requirements of the client's specifications.
Flood testing maximum 48 hours at 50 mm depth.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) con-

taining physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Concrete / brickwork / mortar screeds:
Must be installed on suitably primed, smooth, clean, dry, homogeneous and free from oils and grease, dust and loose or friable particles. Horizontal surfaces must be sloped > 1.5

APPLICATION METHOD / TOOLS

The cold applied bituminous primer SikaBit® P-11 SA or SikaBit® P-12 AE shall be applied onto the substrate (refer to product data sheet) before the first membrane layer as follows:

The membrane is fully to the substrate by the torch-on method using a gas torch. Unroll and position the membrane roll. Roll out half a roll length, heating the underside of the membrane with the gas flame until the polyethylene film and bitumen mass melts. Unroll

the membrane steadily and continuously. A bead of liquid bitumen must be visible on the underside of the roll. The torch on membrane must be firmly pressed onto the substrate in order to avoid air entrapment using a special roller or heavy brush. Repeat this procedure with the second half of the roll. All membranes must be overlapped by a minimum 100 mm the seams must be finished with a roller.

For detailed information regarding application please refer to Method Statement.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Iraq (Sika Trading L.L.C.)

Erbil / Baghdad / Basra

Tel: +96 477 303 74451

info@iq.sika.com

irq.sika.com

PRODUCT DATA SHEET

SikaBit® T-1150 PG SA

December 2020, Version 03.01

020725101000000079

SikaBitT-1150PGSA-en-IQ-(12-2020)-3-1.pdf